

## Dulux AcraTex VENETIAN PLASTER POLISHED STUCCO

AU\_DA02370

Part A	194X2010-22KG
--------	---------------

### Product Overview

Venetian Polished Stucco is an traditional INTERIOR Venetian plaster from yesteryear. It has a classic natural mineral look with a high-gloss finish yielding a multi coloured marble effect. Venetian Plaster Polished Stucco is the perfect choice to decorate high-hand interiors and is widely used in foyers, hotel reception areas and concert halls. It is an eco-friendly product, obtained from selected marble powders and genuine slaked lime baked in wood-fire kilns and aged for 8-10 months.

### Uses And Typical Specifications

<b>Uses</b>	VENETIAN PLASTER POLISHED STUCCO is particularly suited to the preservative restoration of old historical buildings such as churches, palaces or villas interior's; to create surfaces of elevated aesthetic value in all settings whether modern or classic: halls, stairways, bathrooms, living rooms; to add a touch of elegance to the most refined public places such as hotels, restaurants, shops, etc. It is also the ideal solution as a finish on interior restorative dehumidifying plaster.																																						
<b>Typical Systems</b>	<p><b>Typical System</b> Interior Plasterboard  <b>Preparation Guide</b> Refer Full Du Spec specification Sheet</p> <table border="1"> <thead> <tr> <th>Coat</th> <th>Product</th> <th>Spread Rate (m<sup>2</sup>/L)</th> <th>WFT (micron)</th> <th>DFT (micron)</th> </tr> </thead> <tbody> <tr> <td>1st Coat</td> <td>VENETIAN PLASTER QUARTZ PRIMER</td> <td>8</td> <td>125</td> <td>54</td> </tr> <tr> <td>2nd Coat</td> <td>VENETIAN PLASTER POLISHED STUCCO</td> <td>3.69</td> <td>270</td> <td>168</td> </tr> <tr> <td>3rd Coat</td> <td>VENETIAN PLASTER POLISHED STUCCO</td> <td>4.13</td> <td>242</td> <td>150</td> </tr> <tr> <td>4th Coat</td> <td>VENETIAN PLASTER POLISHED STUCCO</td> <td>4.73</td> <td>211</td> <td>131</td> </tr> <tr> <td>5th Coat</td> <td>VENETIAN PLASTER CERA BRILLANTE WAX</td> <td>20</td> <td>50</td> <td>0</td> </tr> <tr> <td colspan="4"><b>Minimum System DFT</b></td> <td><b>503</b></td> </tr> </tbody> </table>				Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)	1st Coat	VENETIAN PLASTER QUARTZ PRIMER	8	125	54	2nd Coat	VENETIAN PLASTER POLISHED STUCCO	3.69	270	168	3rd Coat	VENETIAN PLASTER POLISHED STUCCO	4.13	242	150	4th Coat	VENETIAN PLASTER POLISHED STUCCO	4.73	211	131	5th Coat	VENETIAN PLASTER CERA BRILLANTE WAX	20	50	0	<b>Minimum System DFT</b>				<b>503</b>
Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)																																			
1st Coat	VENETIAN PLASTER QUARTZ PRIMER	8	125	54																																			
2nd Coat	VENETIAN PLASTER POLISHED STUCCO	3.69	270	168																																			
3rd Coat	VENETIAN PLASTER POLISHED STUCCO	4.13	242	150																																			
4th Coat	VENETIAN PLASTER POLISHED STUCCO	4.73	211	131																																			
5th Coat	VENETIAN PLASTER CERA BRILLANTE WAX	20	50	0																																			
<b>Minimum System DFT</b>				<b>503</b>																																			

### Typical Properties

<b>V.O.C Content</b>	0.03	<b>Clean Up</b>	water																				
<b>Sizes</b>	20kg																						
<b>Meets GBCA VOC Requirement?</b>	Yes. Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.																						
<b>Application Conditions</b>	<p><b>Solids By Volume</b> 62</p> <table border="1"> <thead> <tr> <th></th> <th>Min</th> <th>Max</th> <th>Recommended</th> </tr> </thead> <tbody> <tr> <td><b>Wet Film Per Coat (microns)</b></td> <td>211</td> <td>270</td> <td>242</td> </tr> <tr> <td><b>Dry Film Per Coat (microns)</b></td> <td>131</td> <td>168</td> <td>150</td> </tr> <tr> <td><b>Recoat Time (min)</b></td> <td>120</td> <td>180</td> <td></td> </tr> <tr> <td><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td>4.73</td> <td>3.69</td> <td>4.13</td> </tr> </tbody> </table>		Min	Max	Recommended	<b>Wet Film Per Coat (microns)</b>	211	270	242	<b>Dry Film Per Coat (microns)</b>	131	168	150	<b>Recoat Time (min)</b>	120	180		<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	4.73	3.69	4.13		
	Min	Max	Recommended																				
<b>Wet Film Per Coat (microns)</b>	211	270	242																				
<b>Dry Film Per Coat (microns)</b>	131	168	150																				
<b>Recoat Time (min)</b>	120	180																					
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	4.73	3.69	4.13																				
<b>Typical Properties Notes</b>	<p>Note:                      4.73 m<sup>2</sup>/L equates to 0.35 kg/m<sup>2</sup> per coat                      4.13 m<sup>2</sup>/L equates to 0.40 kg/m<sup>2</sup> per coat OR 50m<sup>2</sup> per pail per coat                      3.69 m<sup>2</sup>/L equates to 0.45 kg/m<sup>2</sup> per coat</p>																						

Application Guide	
<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>Interior                             <ul style="list-style-type: none"> <li>– preparation: on civil plaster or old mineral paints as long as they are not powdery, are in good condition and sufficiently rough, apply directly. On supports of the type: gesso, gypsum, plasterboard, old synthetic or powdery paints, stucco smoothing etc, apply a coat of primer to the point of saturation and subsequently a coat of VENETIAN PLASTER MARMORINO. Neutralize in advance with appropriate products the presence of stains of various types or any saline efflorescence. In the case of irregular supports, whether interior or exterior, with uneven absorption rates, restored plaster, stains, etc., the application of a layer of Intocalce with a steel trowel is recommended in order to even out the surface and create the ideal base for even absorption. If you wish to fill the surface to a greater degree or give VENETIAN PLASTER POLISHED STUCCO a more “veined” or “pointed” appearance apply VENETIAN PLASTER POLISHED STUCCO with a steel trowel filling any cracks or imperfections in the surface . When the first layer is completely dry, apply a second layer to level the surface; otherwise apply VENETIAN PLASTER POLISHED STUCCO directly</li> </ul> </li> </ul>
<b>Application Procedure And Equipment</b>	<ul style="list-style-type: none"> <li>Apply one or two layers of VENETIAN PLASTER STUCCO with a steel trowel or spatula letting each layer dry before proceeding in order to obtain a perfectly smooth surface. At this point on the last layer , which has dried slightly, making sure that it is neither completely dry and nor excessively wet, proceed to the polishing by going over the surface repeatedly with a spatula, pressing hard. To confer an increased degree of water repellency and compactness to the surface apply, after about 2/3 hours, with a steel trowel and pressing energetically, a layer of Cere Brillante Wax or a layer of virgin beeswax</li> </ul>

Health And Safety			
<b>MSDS Number</b>	DLX002793	<b>Using Safety Precautions</b>	SAFETY DIRECTIONS: Causes skin irritation. Causes serious eye damage. Keep out of reach of children. Read the label before opening or using. Avoid breathing vapour. Wear protective clothing, gloves, eye/face protection and suitable respirator/dust mask as required. Wash contaminated clothing before re-use. Wash hands, face and all exposed skin thoroughly after handling. Store in a well-ventilated place and away from oxidising agents, acids and foodstuffs. Do not empty into drains.
<b>MSDS Link</b>	<a href="https://go.lupinsys.com/duluxgroup/harms/public/materials/f6361bd249c8123b29eceb05e684f700-published/individual">https://go.lupinsys.com/duluxgroup/harms/public/materials/f6361bd249c8123b29eceb05e684f700-published/individual</a>		
<b>Health Effects</b>	<p>If poisoning occurs, contact a Doctor or Poisons Information Centre (Phone Australia 131 126; New Zealand 0800 764 766). If medical advice is needed, have product container or label at hand.</p> <p>SWALLOWED: If swallowed, rinse mouth with water. Do NOT induce vomiting. Give a glass of water to drink. never give anything by the mouth to an unconscious patient. If vomiting occurs give further water. Seek medical advice.</p> <p>EYE: Immediately irrigate with copious quantities of water for 15 minutes, Eyelids to be held open. Remove clothing if contaminated and wash skin. urgently seek medical assistance. Transport to hospital or medical centre.</p> <p>SKIN: If skin or hair contact occurs, immediately remove any contaminated clothing and flush skin and hair with running water. Continue flushing with water until advised to stop by Poisons Information centre or a Doctor; or for 15 minutes and transport to Doctor or Hospital.</p> <p>INHALED: Remove victim from exposure – avoid becoming a casualty. Remove contaminated clothing and loosen remaining clothing. Allow patient to assume most comfortable position and keep warm. Keep at rest until fully recovered .Seek medical advice if effects persist.</p>		
<b>In the case of emergency, please call 1800 033 111</b>			

Transport And Storage	
<b>Pack A</b>	194X2010-22KG
<b>Size</b> 22kg	<b>Weight</b> 22kg

**Disclaimer**

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427

